



INNOVATIONS FOR LIVING®

PROPINK® L77

PINK FIBERGLAS™ UNBONDED LOOSEFILL INSULATION

**THE PROFESSIONAL'S CHOICE
JUST GOT BETTER.**

- **18% More Coverage Per Bag**
- **Now Approved for Wall Application**





INNOVATIONS FOR LIVING®

PROPINK® L77

PINK FIBERGLAS™ UNBONDED LOOSEFILL INSULATION

Install Premium High Performance that Gives You Finest Total Value

PROPINK® L77 premium high-performance PINK FIBERGLAS™ Unbonded Loosefill now has 18% more coverage per bag! Offering more insulating power per bag, thus increasing your productivity. State-of-the-art engineering and special production processes ensure faster product installation with exceptional quality for a lifetime of reliable performance.



Product Compliance

Owens Corning FIBERGLAS™ loosefill insulation products are thermal tested and labeled in strict accordance with current ASTM loosefill standards. The R-value stated on the label will be achieved when the product is installed according to label specifications.

These products conform to the requirements of ASTM C 764 Type I, Category 2. The surface burning characteristics of these products have been determined in accordance with ASTM E 84:†

- Flame Spread – < 25
- Smoke Developed – < 50

† The surface burning characteristics of these products have been developed in accordance with ASTM E 84, UL 723 or CAN/ULLC-S102. This standard should be used to measure and describe the properties of materials, products, or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use. Values are reported to the nearest 5 rating.

* R-value means resistance to heat flow. The higher the R-value, the greater the insulating power. Ask your seller for the fact sheet on R-values. To get the marked R-value, it is essential that insulation be installed properly.

** As manufactured, fiber glass insulation is resistant to mold growth. However, mold growth can occur on building materials, including insulation, when it becomes contaminated with organic material and when water is present. To avoid mold growth on fiber glass insulation, remove any water that has accumulated and correct or repair the source of that water as soon as possible. Insulation that has become wet should be inspected for evidence of residual moisture and contamination, and any insulation that is contaminated should be promptly removed and replaced.

Install Quality and Peace of Mind in Every Job

When your name is on the line, you need a product that is well known and trusted by customers. You also need a product that provides quality that is tested and proven.

Owens Corning **PROPINK® L77** PINK FIBERGLAS™ Unbonded Loosefill insulation lasts longer and performs better than cellulose loosefill with fewer worries.

When you chose **PROPINK® L77** PINK FIBERGLAS™ Unbonded Loosefill insulation, you can promise your customers peace of mind with these important features:

- **No settling** or deteriorate with age, so there's no danger of losing R-value* over time.
- **Noncorrosive** – Doesn't require fire-retardant chemicals which can leach out, promoting corrosion of pipes, electrical equipment or structural metal attachments.
- **Noncombustible** – Meets all model building codes for noncombustibility.
- **Won't Absorb Moisture** – Moisture reduces insulation effectiveness. Glass fibers resist moisture build-up.
- **Doesn't Support Mold Growth** – Inorganic glass fibers do not support fungus or mold growth.**



L77 ATTIC

Nominal Bag Weight 33lbs.

R-Value	Bags per 1000 Sq.Ft.	Maximum Net Coverage	Minimum Weight/Sq. Ft.	Minimum Thickness inches	Minimum Settled Thickness
R-13	5.5	182.9	0.180	4.75	4.75
R-19	8.1	124.2	0.266	6.75	6.75
R-22	9.4	106.3	0.311	7.75	7.75
R-26	11.2	89.6	0.368	9.00	9.00
R-30	13.0	77.0	0.428	10.25	10.25
R-38	16.8	59.5	0.555	12.75	12.75
R-44	20.1	49.8	0.662	14.75	14.75
R-49	22.6	44.2	0.747	16.25	16.25
R-60	28.5	35.1	0.940	19.50	19.50

L77 WALLS

R-Value	Minimum Thickness	Installed Density lbs per cu. ft.	Maximum Coverage per Bag	Bags per 1000 Sq. Ft.	Minimum weight Lbs. Per Sq. Ft.
13	3.5 (2x4)	1.3	87.0	11.5	0.379
15	3.5 (2x4)	1.5	75.4	13.3	0.438
21	5.5 (2x6)	1.3	55.4	18.1	0.596
24	5.5 (2x6)	1.8	40.0	25.0	0.825

FLOORS

R-Value	Minimum Thickness	Installed Density lbs per cu. ft.	Maximum Coverage per Bag	Bags per 1000 Sq. Ft.	Minimum weight Lbs. Per Sq. Ft.
31	2x8	1.4	39.0	25.6	0.846
39	2x10	1.4	30.6	32.7	1.079
48	2x12	1.5	23.5	42.6	1.406

CATHEDRAL CEILINGS

R-Value	Minimum Thickness	Installed Density lbs per cu. ft.	Maximum Coverage per Bag	Bags per 1000 Sq. Ft.	Minimum weight Lbs. Per Sq. Ft.
28	2x8	1.3	42.0	23.8	0.785
36	2x10	1.3	32.9	30.4	1.002
44	2x12	1.3	27.1	36.9	1.219

† This product shows negligible settling.

Unisol Volu-Matic III machine was used to determine the coverage information above. The machine was set up in 3rd gear, with a 75% open gate and a 3" hose, blowing the wool out in a 10 ft. arc.



INNOVATIONS FOR LIVING®

OWENS CORNING INSULATING SYSTEMS, LLC

ONE OWENS CORNING PARKWAY

TOLEDO, OHIO 43659

1-800-GET-PINK™

www.owenscorning.com



Pub. No. 44426-F. Printed in U.S.A. July 2009. THE PINK PANTHER™ & ©1964-2009 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. ©2009 Owens Corning.